

brunner ::

leather . torro


Ledergruppe C . Cuir groupe C . Leather group C

torro


Ledergruppe C
Cuir groupe C
Leather group C



5/2999




5/2901




5/2902



5/2991




5/2992



5/2993



5/2994




5/2995


Die Farbwiedergabe ist nicht farbverbindlich.
La reproduction des couleurs n'est pas obligatoire.
The colour reproduction may vary.



5/2962




5/2963




5/2969




5/2976



5/2967




5/2970



5/2975




5/2978



5/2979




5/2952




5/2942




5/2943



5/2945




5/2946




5/2949



5/2983



5/2985




5/2986




5/2982



5/2984



5/2987



5/2989

torro

Ledergruppe C

Lederdicke: 1,0 – 1,2 mm,
DIN EN ISO 2589 (DIN 53326)
Lichtechtheit: Stufe Blauskala 5,
DIN EN ISO 105-B02
Weiterreißfestigkeit: > 20 N/mm
DIN EN ISO 3377-1 (DIN 53329)
Dauerfaltverhalten:
20.000 Knickungen, DIN EN ISO 5402
(DIN 53351)
Reibechtheit: > 4, DIN EN ISO 11640
Haftung der Zurichtung: 2,5 N/10 mm
DIN EN ISO 11644/IUF 470
Brandtest: DIN EN 1021 Part I+2

Cuir groupe C

Épaisseur du cuir: 1,0 – 1,2 mm,
DIN EN ISO 2589 (DIN 53326)
Résistance à la lumière: 5,
DIN EN ISO 105-B02
Rupture: > 20 N/mm
DIN EN ISO 3377-1 (DIN 53329)
Résistance au pliage: 20.000 pliages,
DIN EN ISO 5402 (DIN 53351)
Résistance au frottement: > 4,
DIN EN ISO 11640
Adhérence du finissage: 2,5 N/10 mm
DIN EN ISO 11644/IUF 470
Classement au feu: DIN EN 1021
Part I+2

Leather group C

Leather thickness: 1,0 – 1,2 mm,
DIN EN ISO 2589 (DIN 53326)
Lightfastness: 5, DIN EN ISO 105-B02
Tear resistance: > 20 N/mm
DIN EN ISO 3377-1 (DIN 53329)
Permanent folding behaviour:
20.000 flexes, DIN EN ISO 5402 (DIN
53351)
Rubbing fastness: > 4,
DIN EN ISO 11640
Adhesion of finish: 2,5 N/10 mm
DIN EN ISO 11644/IUF 470
Flame resistance: DIN EN 1021
Part I+2